

Physical Properties

Amorphous Polyolefin Tefabloc™ CP

Test method	Test condition	Unit	CP102R
			High
			weatherability
ISO 1183	-	g/cm³	0.94
Reference			0.54
ISO 1133 Reference	230℃, 21.2N	g/10min	1
			_
	1A type, 50mm/min	MPa	34
			. .
Reference		%	15
MPa	70		
ISO 179 Reference	23°C	_	
		kJ/m²	4
		kJ/m³	+
			50
ISO 14782	2mmt	%	4 -
			1.5
Reference		%	0.1
			91
ISO 489	-	-	1
Reference			1.51
ISO 306	50℃/hr, 10N	°C	116
Reference			116
ISO 760	Karl Fischer Method 180℃	%	<0.01
Reference			
	ISO 1183 Reference ISO 1133 Reference ISO 527 Reference ISO 178 Reference ISO 179 Reference ISO 14782 Reference ISO 306 Reference ISO 306 Reference	ISO 1183 Reference - ISO 1133 Reference 230°C, 21.2N ISO 527 Reference 1A type, 50mm/min ISO 178 Reference - ISO 179 Reference 23°C Notched ISO 1479 Reference 23°C Without notch ISO 14782 Reference 2mmt ISO 489 Reference - ISO 306 Reference 50°C/hr, 10N ISO 760 Karl Fischer	ISO 1183 -

- Above evaluations are not entirely ISO compliant.
- Contents in the properties were written in Jan. 2023, and might be revised to improve it without advanced notice.
- Measured values written in the properties are typical without warranty.
- Before using products range, please make sure the legal regulation, conformity and safety limitation in the individual application by testing it in the experiment and checking it in the database list.
- Please pay attention to the patents owned by other companies.
- In the case of application touched to the human body, medical use and food contacting application, please consult us before using our products.