

## ZELAS<sup>™</sup> CP208

Amorphous polyolefin

ver. 2307

## **Product Description**

Zelas<sup>TM</sup> CP207 is a unique amorphous polyolefin designed for the use in medical film, sheet, bottle and molding part application.

- · Rigid, low density, highly transparent polymer with very low absorptive properties
- · Natural color

General		
	<ul> <li>EOG+ Gamma Sterilizable</li> </ul>	<ul> <li>Low moisture+Protein absorption</li> </ul>
Features	Bondable to PE / PP / COP	• Low VOC
Uses:	Medical / Healthcare application	
Appearance:	Transparent, clear	
Form:	• Pellets	
	Sheet / thermo forming	
Typical process methods:	Injection molding	

## Technical Information<sup>1</sup>

<sup>1</sup>Typical values are not to be construed as specifications.

Physical	Typical Value	Unit	Test Method
Melt Flow Rate (230°C, 2,16 kg)	1	g/10min	ISO 1133
Density	0.93	g/cm <sup>3</sup>	ISO 1183, Method A
Water absorption	<0.01	%	ISO 760
Haze	2.0	%	ISO 14782, 2mmt
Mechanical		Unit	Test Method
Tensile strength	30	MPa	- ISO 527
Tensile elongation	15	%	
Flexural Modulus	1600	MPa	ISO 178
Charpy (unnotched)	>40	kJ/m <sup>2</sup>	ISO 179
Thermal		Unit	Test Method
Vicat	116	deg C	ISO 306



MITSUBISHI Mitsubishi Chemical Corporation

1-1, Marunouchi 1-chome, Chiyoda-ku, Tokyo 100-8251, Japan

ZELAS<sup>™</sup> is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is, to the best of our knowledge, true and accurate based on tests or experience that we believe are reliable, but all recommendations or suggestions are made without any guarantee, since the conditions of use are beyond our control. There is no warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose of our products. In submitting this information, no liability is assumed by us and no license or other rights express or implied are given to the user with respect to any existing or pending patent, patent applications or trademarks. The observance of all legal regulations and patents is the responsibility of the user. We shall not be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, tort or strict liability.

© 2005 Mitsubishi Chemical Corporation. All rights reserved